

ROMPOX[®] - 1080

Tested substance	12 hrs	48 hrs	7 days
Ammonia 25 %	+	+	+
Ammonia 10 %	+	+	+
Ammonia 5 %	+	+	+
Chloroform conc.	-	-	-
Chloroform 50 %	+	+	+
Chromoxide 50 %	-	-	-
Chromoxide 20 %	x	x	x
Chromoxide 10 %	x	x	x
Chromoxide 5 %	x	x	x
Citric acid 20 %	x	x	x
Citric acid 10 %	x	x	x
Citric acid 5 %	+	+	+
Acetic acid 10 %	+	+	x
Acetic acid 5 %	+	+	000
Ethanol	+	+	-
Formaldehyd solution 36,5 %	+	+	+
Formaldehyd solution 10 %	+	+	+
Potassium hydroxide 10 %	+	+	x
Potassium hydroxide 50 %	+	+	+
Lactic acid 1 %	x	x	x
Lactic acid 5 %	x	x	x
MPA	+	+	+

Tested-substance	12 hrs	48 hrs	7days
Sodium hydroxide 10 %	x	x	x
Sodium hydroxide 50 %	x	x	x
Sodium chloride 5 %	+	+	+
Sodium chloride 30 %	+	+	+
Sodium chloride 50 %	+	+	+
Ortho – Phosphoric acid 85 %	-	-	-
Ortho – Phosphoric acid 42,5 %	x	oo	oo
Ortho – Phosphoric acid 20 %	x	x	x
Ortho – Phosphoric acid 10 %	x	x	x
Oxal acid 5 %	x	x	x
Oxal acid 10 %	x	x	x
Nitric acid 65 %	-	-	-
Nitric acid 32,5 %	x	oo	oo
Nitric acid 16 %	x	x	x
Nitric acid 8 %	x	x	x
Hydrochloric acid 37 %		-	-
Hydrochloric acid 20 %		x	oo
Hydrochloric acid 10 %		x	x
Hydrochloric acid 5 %		x	x
Sulphuric acid 96 %	-	-	-
Sulphuric acid 50 %	x	oo	oo
Sulphuric acid 25 %	x	x	x
Sulphuric acid 10 %	x	x	x

Tested-substance	12 hrs	48 hrs	7 days
Sulphuric acid 5 %	x	x	x
Hydrogen peroxide 3 %	+	+	+
Xylol	+	+	+
Butanol	+	+	oo
Butylacetate	+	oo	-
Isopropylalcohol	+	+	oo
Tuluol	+	oo	-
Ethylene-alcohol	+	+	oo
Butylglycolacetate	+	oo	-
Butyldiglycolacetate	+	oo	-
Ethylbenzol	+	oo	oo

Key:

Non-resistant:	-
Resistant:	+
Resistant/discolouration:	x
Resistant/discolouration/light bubble formation:	o
Discolouration/softening:	oo
Discolouration/light damage:	xx
Softening:	ooo

NOTE:

Our recommendations, which are given to assist buyers & endusers, are based on experience and correspond to the current levels of knowledge in science and practice, however they are not binding and have no legal force. It is recommended adapting methods and quantities of product to the local needs (Issue 2004-08-25) REV 04

CB_DE_ROMPOX_1080.doc