

ROMPUR[®] - 2705

Tested substance	Value
Formic acid 85%	-
Formic acid 50%	-
Formic acid 10%	-
Formic acid 5%	-
Formic acid 3%	0
Ammonia 10%	+
Ammonia 25%	+
Ethyl alcohol	-
Ethyl alcohol 10%	0
Acetone	-
Petrol	+
Benzol	-
Boric acid 3% at 30°C	+
Butyl acetate	-
Desinfectant	+
Dibutyl phthalate	
Diesel oil	+
Acetic acid 5%	-
Acetic acid 10%	-
Acetic acid 30%	-
Acetic acid 60%	-
Acetic acid 80%	-
Caustic potash solution	up to 3% +
Saline solution. 10%	+
Enamel petrol	+
Methanol	-
Methylene chloride	-
Lactic acid/butyric acid/acetic acid at 1%	+
Sodium chloride 3%	+
Sodium chloride 30%	-

Page 2 of chemical resistance list ROMPUR 2705

Tested substance	Value
Phosphoric acid 20%	+
Phosphoric acid 45%	+
Phosphoric acid Konz.	-
Castor oil	+
Raw oil	+
Nitric acid 5%	-
Nitric acid 10%	-
Nitric acid 20%	-
Nitric acid 30%	-
Nitric acid 40%	-
Nitric acid 60%	-
Saline solution conc.	-
Hydrochloric acid 10%	+
Hydrochloric acid 20%	+
Hydrochloric acid 30%	+
Hydrochloric acid 37%	-
Sulphuric acid 5%	+
Sulphuric acid 10%	+
Sulphuric acid 20%	+
Sulphuric acid 30%	+
Sulphuric acid 40%	+
Sulphuric acid 50%	-
Sulphuric acid 80%	-
Sulphuric acid steaming	+
Distilled water	0
Wine	+
Xylol	-
Citric acid	up to 10% +
Sugar solution 30%	+

Key:
 ++ = very good resistance
 + = resistant
 + > - = tending towards non resistant
 - = non resistant

NOTE:

Our recommendations, which are given to assist buyers & end users, are based on our experience and correspond to the current levels of knowledge in science and practice, however they are not binding and have no legal force. It is recommended adapting methods and quantities of product to the local needs. If necessary a sample surface should be laid beforehand. (Issue 2006-10-10) REV 03

CB_GB_ROMPUR_2705.doc