

## ROMPOX® 1005 coating

High gloss, abrasion resistant, layer thickness 2,0 mm

Item	Description	Quantity Unit	Unit price €/Unit	Total price €
1.	<p><b>Preparation work on cement bound and metal surfaces:</b> The surface must be even, dry and free of oil, grease and dust. Loose particles and other dirt must be removed. In most cases, the surface should be shotpeened and then primed. In some cases it may be necessary to carry out grinding or milling. The minimum adhesion strength of the concrete needs to be &gt; 1,5 N/mm<sup>2</sup>. Residual moisture must be &lt; 4% (CM machine). The concrete surface must be evened out using ROMPOX® 1505 as either a primer or scraping filler, in order to achieve an extremely smooth surface. Cement surfaces with a high residual moisture ≤ (6%) must be treated with ROMPOX® 1506. Highly porous surfaces need to be primed twice! Metal surfaces should be treated according to the Swedish norm SA 2 ½ and then primed with ROMPOX® 1101.</p>			-on the part of the contractor-
2.	<p><b>Priming of cement bound surfaces:</b> A high quality, solvent free, epoxy resin primer is applied to the prepared surface using a 1 lip rubber squeegee and a fur roller. Material: <b>ROMPOX® 1505 EP primer</b> Consumption: 0,3 kg/m<sup>2</sup> Price: €/kg</p>		0,00	0,00
3.	<p><b>Scraping filler (if required):</b> ROMPOX 1005 needs an extremely even surface. That is why the following scraping filler is required, even with only slight surface roughness. The scraping filler is applied using a 1 lip rubber squeegee and a fur roller. Material: <b>ROMPOX® 1505 EP primer</b> Consumption: approx. 0,5 kg/m<sup>2</sup> binding agent per mm layer thickness with <b>ROMEX® 3209 filler material</b> 1:1,5 mixed Price: €/kg</p>		0,00	0,00
4.	<p><b>Coating:</b> The coating is applied to the prepared surface using a squeegee or smoothing trowel. Material: <b>ROMPOX® 1005 coating</b> Consumption: 2,500 kg/m<sup>2</sup> Price: €/kg</p> <p>After application of ROMPOX® 1005 coating, the whole surface needs to be areated using a metal pinfeed platen.</p>		0,00	0,00
<b>Cost of materials</b>			<b>0,00</b>	<b>0,00</b>

# Standard specifications for sales

Standard specifications for sales

## Page 2 of standard specifications for sales ROMPOX 1005 coating

Item	Description	Quantity unit	Unit price €/Unit	Total price €
	Carried over from page 1		<b>0,00</b>	<b>0,00</b>
5.	<b>Labour costs:</b> <ul style="list-style-type: none"><li>- Building site preparation/tools and equipment</li><li>- Priming</li><li>- Scraping filling</li><li>- Coating</li></ul>		0,00 0,00 0,00 0,00	0,00 0,00 0,00 0,00
	<b>Cost of materials</b>		<b>0,00</b>	<b>0,00</b>

Our recommendations, which are given to assist buyers & endusers, are based on our experience and correspond to the current levels of knowledge in science and practice, however they are not binding and have no legal force. It is recommended adapting methods and quantities of product to the local needs. If necessary a sample surface should be laid beforehand.