

# Overview of the water permeability

## ROMEX® Paving Joint Mortar

Product name	Water permeability value		Water permeability acc. DIN 18130	Water permeable acc. to „Leaflet on water permeable pavements and roads“ by Research institute for road and traffic (Germany) Issue 2013
ROMPOX® - EASY	3,91 x 10 <sup>-3</sup> m/s	ca. 12 l/min/m <sup>2</sup>	highly permeable	permeable
ROMPOX® - 1K-POWERFUGE	6,66 x 10 <sup>-4</sup> m/s	ca. 2 l/min/m <sup>2</sup>	highly permeable	permeable
ROMPOX® - DRAIN	4,96 x 10 <sup>-3</sup> m/s	ca. 15 l/min/m <sup>2</sup>	highly permeable	permeable
ROMPOX® - DRAN plus	4,91 x 10 <sup>-3</sup> m/s	ca. 15 l/min/m <sup>2</sup>	highly permeable	permeable
ROMPOX® - D1	7,50 x 10 <sup>-4</sup> m/s	ca. 2,3 l/min/m <sup>2</sup>	highly permeable	permeable
ROMPOX® - D1 plus	7,50 x 10 <sup>-4</sup> m/s	ca. 2,3 l/min/m <sup>2</sup>	highly permeable	permeable
ROMPOX® - FLEX-JOINT	1,63 x 10 <sup>-4</sup> m/s	ca. 0,98 l/min/m <sup>2</sup>	highly permeable	permeable
ROMPOX® - D2000	9,06 x 10 <sup>-6</sup> m/s	ca. 0,03 l/min/m <sup>2</sup>	permeable	not permeable
ROMPOX® - D3000	1,07 x 10 <sup>-3</sup> m/s	ca. 3,2 l/min/m <sup>2</sup>	highly permeable	permeable
ROMPOX® - TRAFFIC V2	4,78 x 10 <sup>-6</sup> m/s	ca. 0,015 l/min/m <sup>2</sup>	permeable	not permeable